PAPER • OPEN ACCESS

Manufacturing of New Welding Fluxes Using Silicomanganese Slag

To cite this article: Roman E Kryukov et al 2017 IOP Conf. Ser.: Mater. Sci. Eng. 253 012007

View the article online for updates and enhancements.

Manufacturing of New Welding Fluxes Using Silicomanganese Slag

Roman E Kryukov¹, Nikolay A Kozyrev¹, Olga A Kozyreva², Aleksander A Usoltsev¹

¹Siberian IndustrialStateUniversity 654007, Russia, Kemerovo region, Novokuznetsk, Kirova street, 42 ² KemerovoStateUniversity, 6, Krasnay street, Kemerovo, 650000

E-mail: a Kozyrev na@mtsp.sibsiu.ru

Abstract. There were developed the composition and manufacturing technology of new welding flux using industrial products such as slag of silicomanganese production. The effect of fractional composition on welding and fabrication characteristics was studied. It was found that using of small-sized fracture of welding flux at a rate of 30-40% decreases the oxide non-metallic impurity rating of the weld and herewith doesn't affect its constituents.

To increase technical-and-economic indexes it was suggested to mix small-sized fracture and water glass. The use of ceramic flux made by mixing the dust fraction of silicomanganese slug with fraction size less than 0.45 mm and water glass provides the decrease of non-metallic impurity rating of the weld. Herewith the increase of its content from 15 to 40% doesn't have a significant influence on the non-metallic impurity rating of the weld and its constituents.

Introduction

Great attention in the world is paid to the issues of production, research and development of new welding fluxes [1-18]. It was proposed to use the slag of silicomanganese production for welding flux manufacturing [19, 20], the technology is protected by patents [21, 22]. The possibility of effective use of slag of silicomanganese production for welding flux manufacturing considered in this paper.

Methods and materials

For the flux manufacturing was used the slag of silicomanganese production which chemical composition is presented in table 1. Alsointhefirstseries of experiments the possibility of use of differentslag fractions ratio was examined (table 2). Double-sided flux plain butt welding was carried out on the samples of 500×75 mm size and 16 mm thick made of sheet and plate steel type 09G2S. The welding process was performed with wire Sv-08GA with the use of welding machineASAW-1250 in modes: $I_{weld} = 700 \text{ A}$; $U_{arc} = 30 \text{ V}$; $V_{weld} = 35 \text{ m/h}$.

					U		0			
				Со	ntent, %					
Al_2O_3	CaO	SiO ₂	FeO	MgO	MnO	F	Na ₂ O	K ₂ O	S	Р
5.91-	22.85-	46.46-	0.27-	6.48-	8.01-	0.28-	0.26-	0.62	0.15-	0.01
9.62	31.70	48.16	0.81	7.92	8.43	0.76	0.36	0.02	0.17	0.01

Table 1 – Chemical composition of the slag of silicomanganese production



Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd

IOP Publishing

Samples were cut of the welded plates and the X-rays pectrometry of weld chemistry and metallographical tests of weld metal were conducted. Chemical composition of welding fluxes is presented in table 3. Chemical composition of slag crust is presented in table 4, chemical composition of weld metal is presented in table 5.

Sample	Ratio, %, of fractions, mm
1	100 % of fraction 0.45 – 2.5
2	95 % of fraction 0.45 – 2.5 + 5 % of fraction<0.45
3	90 % of fraction 0.45 – 2.5+ 10 % of fraction< 0.45
4	85 % of fraction 0.45 – 2.5 + 15 % of fraction < 0.45
5	80 % of fraction 0.45 – 2.5+ 20 % of fraction< 0.45
6	70 % of fraction 0.45 – 2.5+ 30 % of fraction< 0.45
7	60 % of fraction $0.45 - 2.5 + 40 %$ of fraction < 0.45
8	60 % silicomanganese slag + 40 % water glass
9	70 % silicomanganese slag + 30 % water glass
10	80 % silicomanganese slag + 20 % water glass
11	85 % silicomanganese slag + 15 % water glass

Table 2 – Fraction and component composition of fluxesin question

Sample					Conte	ent, %				
	Al_2O_3	CaO	SiO ₂	FeO	MgO	MnO	F	Na ₂ O	S	Р
8	5.29	25.84	51.75	0.55	5.02	7.39	0.36	4.66	0.12	0.01
9	5.48	26.68	51.73	0.57	5.16	7.59	0.39	4.19	0.13	0.01
10	5.88	25.53	52.53	0.56	5.07	7.75	0.31	4.07	0.13	0.01
11	6.55	26.81	51.14	0.56	5.78	8.10	0.35	2.62	0.14	0.01

Table 3 – Chemical composition of welding fluxes

Table $4 - 6$	Chemical	composition	of slug crusts
		1	U

G 1					С	ontent,	%				
Sample	MnO	SiO ₂	CaO	MgO	Al ₂ O ₃	FeO	Na ₂ O	K ₂ O	F	S	Р
1	7.90	46.04	23.38	6.77	10.08	2.07	0.37	0.65	0.73	0.13	0.01
2	7.87	45.58	31.82	6.62	6.77	1.35	0.26	absent	0.32	0.11	0.01
3	7.83	44.54	23.84	6.43	9.64	3.59	0.37	0.65	0.69	0.12	0.008
4	8.09	45.91	31.15	6.60	6.79	1.39	0.27	absent	0.29	0.11	0.01
5	7.93	45.67	23.84	6.54	9.87	2.86	0.37	0.65	0.72	0.12	0.008
6	8.16	45.74	29.39	6.22	6.93	1.99	0.26	absent	0.36	0.12	0.01
7	8.23	45.52	29.12	6.29	6.65	1.88	0.28	absent	0.26	0.12	0.01
8	8.19	48.79	24.42	4.82	5.14	2.45	3.64	absent	0.35	0.09	0.01
9	8.29	49.92	26.12	5.37	5.60	2.64	3.25	absent	0.37	0.10	0.01
10	8.16	48.25	26.32	5.22	6.02	2.17	2.12	absent	0.33	0.12	0.01
11	8.18	48.09	27.24	5.67	6.36	1.97	1.64	absent	0.34	0.12	0.01

						0 0 0 - 0 - 0								
Sampla	Content, %													
Sample	С	Si	Mn	Cr	Ni	Cu	V	Nb	Al	S	Р			
1	0.09	0.71	0.51	0.03	0.10	0.11	0.001	0.014	0.023	0.018	0.012			
2	0.08	0.54	1.33	0.04	0.05	0.08	0.003	0.014	0.015	0.008	0.008			
3	0.09	0.61	1.49	0.04	0.11	0.11	0.01	0.013	0.018	0.016	0.010			
4	0.07	0.45	1.24	0.02	0.05	0.07	0.002	0.014	0.014	0.006	0.007			
5	0.08	0.66	1.42	0.03	0.10	0.11	0.002	0.015	0.023	0.018	0.012			
6	0.08	0.61	1.42	0.02	0.06	0.08	0.003	0.014	0.029	0.010	0.011			
7	0.08	0.59	1.39	0.02	0.02	0.05	0.004	0.018	0.091	0.014	0.009			
8	0.05	0.52	1.25	0.02	0.04	0.05	0.003	0.017	0.020	0.005	0.007			
9	0.03	0.51	1.23	0.02	0.04	0.06	0.002	0.017	0.017	0.007	0.008			
10	0.06	0.53	1.31	0.02	0.04	0.06	0.004	0.016	0.018	0.012	0.009			
11	0.09	0.52	1.31	0.02	0.04	0.06	0.003	0.015	0.013	0.010	0.008			

Table 5 – Chemical co	nposition	of weld	metal
-----------------------	-----------	---------	-------

Metallographical tests were conducted on micro sections without etching by means of optical microscope OLYMPUSGX-51 with optical magnification 100. Metallographical tests of metal structure in weld zone were conducted by means of optical microscopeOLYMPUSGX-51 in a bright-field in the magnification range of 500 after the etching of the samples surface in 4% nitricacid solution. Grain size was determined in accordance with GOST 5639 – 82.

Results

Theresults of analysis for presence of non-metallic inclusions in the weld zone carried out in accordance with GOST 1778-70, are presented in the figure 1 and in the table 6.



Microstructures of weld metal are presented in the figure 2.



Samples were cut of the welded plates and their mechanical properties were determined. The results obtained by investigation of mechanical properties show the increase of impact strength (Figure 3).

The analysis of samples' mechanical properties shows that the optimal content of dust fraction with size less than 0.45 mm is 20-30%. This content of dust fraction with size less than 0.45 mm delivers the profitable set of mechanical properties of the samples cut of the welded plates.

In the weld metal structure of all samples' welds there is a ferrite presented in the form of unequiaxed grains elongated along the line of heat removal. There can be seen the transition from ferrite-pearlite uniform structure to the Widmanstatten ferrite-pearlite structure. However, relevant variation of grain sizes on a grain-size scale was not observed (table 6, 7).



Fig. 3.The effect of dust fraction content (fraction size less than 0.45 mm) in the flux on the impact strength

In these cond series of experiments the possibility of use of ceramic flux made of water-glass-bonded silicomanganese slug's dust with fraction sizeless than 0.45 mm was studied. The production technique involved mixing silicomanganese slug and water glass in different proportions (table 2), drying, crush in gand size grading to get fractions 0.45-2.5 mm.

	Tuble 0 Ttoli lile		5110
Sampla	Non-me	tallic inclusions, scale nu	mber
Sample	Non deflecting silicates	brittle silicates	spot oxides
1	4b; 3b; 4a	3b	1a
2	2b; 1b; 3a; 4a	absent	1a; 2a
3	4b; 2b	absent	1a; 2a
4	2b; 4b	absent	1a; 2a
5	4b; 5b; 3b	absent	1a; 2a
6	2b; 1b; 2a; 2,5a	absent	1a; 2a
7	2b; 2a; 2,5a	absent	1a; 2a
8	2b; 1b; 2a; 2,5a	absent	1a
9	2b; 1b; 2a; 2,5a	absent	1a
10	2b;1b; 2a; 2,5a	absent	1a; 2a
11	2b; 2,5a	absent	1a, 2a

Table 6 - Non-metallicinclusions in weld zone

Table 7 – Welds' grain size according toGOST 5639-82

Sample	Grain size on grain size scale
1	<u>№</u> 4, №5
2	№5, №4
3	№4, №5, №6
4	<u>№</u> 4
5	№5, №4
6	<u>№</u> 4
7	<u>№</u> 4
8	№5, №4
9	№4, №5
10	<u>№</u> 4
11	№4, №5

The analys is of the mechanical properties of the samples cut of welded plates allowed to determine the optimal content of water glass in the flux (up to 20-30%) to achieve the profitable set of mechanical properties of the samples cut of the welded plates (figures 4, 5).

However, the examined fluxes are oxidizing fluxes and are created on the principles of siliconmanganese-oxidation-reduction reactions, therefore resultants of such reactions are oxidic compound of silicon and manganese. Consequently the non-metallic impurity rating of weld increases and hence the physical and mechanical properties decreases, especially at low temperatures. To decrease the impurity rating of weld and to increase mechanical properties we investigated the possibility of introduction of previously developed carbon and fluorine containing admixture FD–UFS in the new flux.



Fig. 4. The effect of water glass content in the flux on percentage elongation



Fig. 5. The effect of water glass content in the flux on the impact strength

In the experiments flux-admixture was added at the ratio of 2, 4, 6, 8 % accordingly. Chemicalcomposition of examined mixtures is presented in table 8, composition of slug crusts is presented in table 9, chemical composition of welds' metal is presented in table 10.

FD–UFS content in the flux, %	FeO	MnO	Ca	SiO ₂	Al ₂ O ₃	MgO	Na ₂ O	K ₂ O	S	Р	ZnO	F
2	0.40	8.01	15.80	50.08	11.55	7.39	0.77	0.63	0.22	0.008	0.002	1.30
4	0.91	7.90	17.72	46.63	10.32	6.63	1.10	0.68	0.24	0.01	absent	1.95
6	0.81	7.68	16.79	43.64	11.27	5.71	2.25	0.65	0.34	0.01	0.003	4.04
8	0.46	7.46	16.00	43.64	11.86	5.56	2.30	0.60	0.33	0.01	0.002	3.96

Table 8 – Chemical composition of examined flux mixtures, %

FD–UFS												
content in the	FeO	MnO	Ca	SiO ₂	Al_2O_3	MgO	Na ₂ O	K_2O	S	Р	ZnO	F
flux, %												
2	2.21	7.25	15.55	38.09	9.39	8.63	0.49	0.57	0.12	0.006	0.002	0.94
4	2.28	7.39	16.90	42.00	9.76	5.77	0.76	0.62	0.15	0.008	0.002	1.12
6	2.24	7.20	16.06	39.94	11.15	7.14	1.09	0.60	0.17	0.008	0.002	1.53
8	2.36	7.14	14.70	42.87	12.40	5.57	1.34	0.57	0.20	0.008	0.002	1.88

Table 9 – Chemical composition of slug crusts, %

Therefore, the metal of the weld which has been made with flux without admixtures has the highest non-metallic impurity rating. The introduction of admixture FD–UFS decreases the non-metallic impurity rating and also decreases the impurities' size and number. Speaking of the examined ratio, the highest effect on the non-metallic impurity rating has the 8% amount of admixture.

FD–UFS		Mass fraction of the element %										
content in the flux, %	С	Si	Mn	Cr	Ni	Cu	Nb	Al	S	Р		
2	0.09	0.62	1.40	0.02	0.06	0.09	0.014	0.023	0.020	0.008		
4	0.10	0.60	1.34	0.02	0.07	0.08	0.010	0.013	0.023	0.009		
6	0.12	0.66	1.43	0.02	0.06	0.10	0.011	0.012	0.027	0.008		
8	0.13	0.65	1.36	0.03	0.06	0.09	0.013	0.013	0.024	0.008		

Table 10 –	Chemical	comp	osition	of welds'	metal
14010 10		• • • • • • • • •			

The results of analys is for presence of non-metallic inclusions in the weld zone carried out in accordance with GOST 1778 - 70 are presented on figure 6 and in the table 11.



Fig. 6.Non-metallicinclusions in the weld zone of the samples with admixture ratio, %: a) 2; b) 4; c) 6; d) 8

FD–UFS content in the	Non-metallic inclusions, scale number				
flux, %	Non deflecting silicates	brittle silicates	spot oxides		
2	2b, 4b, 5a	absent	1a, 2a		
4	2b, 4b	absent	1a, 2a		
6	2b, 4b, 1b	absent	1a, 2a		
8	2b	absent	1a, 2a		

Tal	ble	11	. — Ì	Non-met	talli	cincl	lusio	onsinwel	ldzone
-----	-----	----	-------	---------	-------	-------	-------	----------	--------

Microstructure of samples' welds is presented on figure 7. It was found out that introduction of admixture at a rate no more than 8% has no effect on the size and morphology of constituents.



Fig. 7.Microstructureof welds of the samples with admixture ratio, %: a) 2; b) 4; c) 6; d) 8

The examination of mechanical properties has shown that as the amount of admixture increases the level of properties also increases (figure 8). The conducted researches formed the basis for RF patents [21, 22].



Fig. 8.Effect of admixture FD–UFS ratio in the flux on the impact strength (KCV at T=-20 °C)

Conclusions

1. The possibility in principle of use of slag of silicomanganese production for welding flux manufacturing was shown.

2. It is possible to use in the fluxes up to 30% of small-sized fracture(less than 0.45 mm). This content of dust fracture in the flux is optimal to achieve the profitable set of mechanical properties of the samples cut of the welded plates.

3. The optimal content of water glass in the flux allows to achieve the profitable set of mechanical properties is 20-30%.

4. To decrease the non-metallic impurity rating of weld and to increase mechanical properties of the weld it was suggested to introduce in the fluxes carbon-fluorine containing admixture FD–UFS at the ratio 2-8%. The introduction of admixture decreases the non-metallic impurity rating and also decreases the impurities' size.

References

[1] R. Q. Puchol, J. R. Blanco, L. P. Gonzalez, G. C. Hernández, C. R Gómez Pérez. The influence of the air occluded in the deposition layer of flux during automatic welding: a technological aspect to consider in the quality of the bead // Welding International. 2009. Vol. 23. N 2. P. 132 – 140.

[2] A.C.Crespo, R.Q.Puchol, L.P.Goncalez, L.G.Sanchez, C.R.Gomez Perez, E.D.Cedre, T.O.Mendez and J.A. Pozol Obtaining a submerged arc welding flux of the MnO - SiO2 - CaO - Al2O3 - CaF2 system by fusion // Welding International. 2007. Vol. 21. No 7. P. 502 - 511.

[3] A.C.Crespo, R.Q.Puchol, L.P.Goncalez, L.G.Sanchez, C.R.Gomez Perez, G.Castellanos, E.D.Cedreand T.Ortíz. Study of the relationship between the composition of a fused flux and its structure and properties // Welding International. 2009. Vol. 23. N 2. P. 120 – 131.

[4] Golovko V.V., Potapov N.N. Special features of agglomerated (ceramic) fluxes in welding // Welding International. 2011. Vol. 25. № 11. P. 889 – 893.

[5] VolobuevYu.S., Volobuev O.S., Parkhomenko A.G., Dobrozhela E.I., Klimenchuk O.S. Using a new general-purpose ceramic flux SFM-101 in welding of beams // Welding International. 2012. Vol. 26. № 8. P. 649 – 653.

[6] VolobuevYu.S.,Surkov A.V.,Volobuev O.S., Kipiani P.N.,Shestov D.V., Pavlov N.V.,Savchenko A.I. The development and properties of a new ceramic flux used for reconditioning rolling stock components // Welding International. 2010. Vol. 24. N_{0} 4. P. 298 – 300.

[7] Potapov N.N.,Kurlanov S.A. A criterion for evaluating the activity of fused welding fluxes // Welding International. 1987. Vol. 1. № 10. P. 951 – 954.

[8] Babushkin P.L., Persits V.Yu. Determination of hydrogen in the form of moisture in basic electrode coatings and fluxing materials in metallurgical production // Welding International. 1991. Vol. 5. N_{2} 9. P. 741 – 742.

[9] Pavlov I.V., Oleinichenko K.A. Regulating generation of CO by varying the composition of ceramic fluxes // Welding International. 1995. Vol. 9. N_{0} 4. P. 329 – 332.

[10] Chigarev V.V.,Kosenko A.A. Regulating the silicon-reduction process in welding under ceramic fluxes with an active deoxidising agent // Welding International. 1994. Vol. 8. N_{2} 10. P. 808 – 809.

[11] Kurlanov S.A., Potapov N.N, Natapov O.B. Relationship of physical and welding-technological properties of fluxes for welding low-alloy steels // Welding International. 1993. Vol. 7. № 1. P. 65 – 68.
[12] Bublik O.V., Chamov S.V. Advantages and shortcomings of ceramic (agglomerated) fluxes in comparison with fused fluxes used for the same applications // Welding International. 2010. Vol. 24. № 9. P. 730 – 733.

[13] Gur'ev S.V.,PletnevYu.M.,Murav'ev I.I. Investigation of the properties of welded joints produced by welding in a gas mixture and under a flux // Welding International. 2012. Vol. 26. $N_{0.8}$ P. 646 – 648.

[14] Parshin S.G. Using ultrafine particles of activating fluxes for increasing the productivity of MIG/MAG welding of steels // Welding International. 2012. Vol. 26. № 10. P. 800 – 804.

[15] A.C. Crespo, R.Q. Puchol, L.P. Goncalez, C. R Gómez Pérez, L.G. Sanchez, G.E. Vielsa, A.C. Sánchez Carbothermic reduction of pirolusite to obtain carbon-bearing ferromanganese and slag suited to the development of welding materials // Welding International. 2005. Vol. 19. № 7. P. 544 – 551.

[16] Barmin L.N. Effect of the composition of flux and welding wire on the properties of deposited metal of 05N4MYu type // Welding International. 1989. Vol. 3. № 2. P. 109 – 111.

[17] KazakovYu.V.,Koryagin K.B.,Potekhin V.P. Effect of activating fluxes on penetration in welding steels thicker than 8 mm // Welding International. 1991. Vol. 5. № 3. P. 202 – 205.

[18] Potapov N.N.,Feklistov S.I.,VolobuevYu.S.,PotekhinV.P. A method of selecting fused fluxes in welding pearlitic–ferritic steels // Welding International. 2009. Vol. 23. № 10. P. 800 – 803.

[19] Kozyrev N.A., Kryukov R.E., Kozyreva O.E., Lipatova U.I., Filonov A.V. Production of Welding Fluxes Using Waste Slag Formed in Silicomanganese Smelting // IOP Conference Series: Materials Science and Engineering. 2016. Vol. 125. P. 1 – 6: All-Russia Scientific and Practical Conference on Materials Treatment: Current Problems and Solutions 26 – 28 November 2015, Yurga, Russia.

[20] Kozyrev N.A., Kryukov R.E., Lipatova U.I., Kozyreva O.E. On the use of slag from silicomanganese production for welding flux manufacturing // IOP Conf. Series: Materials Science and Engineering. 2016. Vol. 150. P. 1 - 9.

[21] Kryukov N.E., Kryukov E.N., Kozyrev N.A., Kryukov R.E., Kozyreva O.A.; JSC «Novokuznetsk plant of reservoir metalware named after N.E. Kryukov»: «Welding flux», RF Patent 2576717, 05 June 2014.

[22] Kryukov N.E., Kryukov E.N., Kozyrev N.A., Kryukov R.E., Kozyreva O.A.; JSC «Novokuznetsk plant of reservoir metalware named after N.E. Kryukov»: «Welding flux»: RF Patent 2579412, 05 June 2014.